

## #105AF BULLDOG® DOUBLE COVERAGE CEMENT



### DESCRIPTION

A heavy brush consistency cold process cement manufactured with the finest blends of petroleum asphalts and solvents, combined with select mineral fillers and other stabilizers to create a smooth adhesive with excellent tack capabilities. Requires no heating or thinning before use. Its adhesive qualities prevents moisture from seeping through laps or poorly impregnated roofing papers. SPECIFICATIONS: ASTM D 3019, TYPE III

### USES

Most frequently used in application of double coverage or wide selvage edge roofing as a cold process adhesive. It is also used between successive layers of roofing felts or as a base and top coat in which polyester mat is utilized as a reinforcing membrane.

### METHODS AND RATE OF APPLICATION

Apply with brush, roller or spray to dry, dirt free surfaces at rate of 2 gallons per 100 square feet (.8 liters per M<sup>2</sup>) when used to blind nail or cement laps of roll roofing. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	490 POUNDS
5 Gallon Pail	43 POUNDS
1 Gallon (6 to Carton)	54 POUNDS

### TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	70.0
Volatile Solvent, % by Weight.....	29
Mineral Filler and/or other Stabilizers, % by Weight.....	12.0
Asphalt Solids, % by Volume.....	58.0
Water Content, % by Volume.....	0.5
Net Weight Per Gallon, Pounds.....	8.2
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon.....	10 Mils
Dry Time @ Recommended Rate of Application.....	2 Days
Service Temperature.....	-30°F to +160°F
Flash Point, in Degrees F, C.C., ASTM D 93.....	104
Strength of Lap, 24 Hours, ASTM D 3019.....	30.0 Minimum
Condition in Container.....	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

**The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.**

**DISCLAIMER OF WARRANTIES.** The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY  
196 WEST 5TH ST  
P.O. BOX 58  
BAYONNE, NJ 07002  
PHONE (201) 339-0855  
FAX (201) 339-8320  
www.palmerasphalt.com