

PRODUCT DATA SHEET

#106AF BULLDOG® FIBER ROOF COATING



DESCRIPTION

BULLDOG Fiber Roof Coating is a black, asphalt based, fibered coating used to coat aged built-up asphalt roofs, metal roofs and modified bitumen roofs. Use of BULLDOG Roof Coating may add years of life to the roof. This coating is elastic and adheres well to appropriate surfaces and will not run or become brittle and crack. BULLDOG Fiber Roof Coating comes ready for use. It requires no heating or thinning. SPECIFICATIONS: ASTM D 4479, Type I Federal Specification SS-A-694D (Except Non-Asbestos)

USES

Used to periodically recoat built-up roofing surfaces as part of a preventative roof maintenance program. Properly applied the coating will not alligate, check or bubble. May also be used to damp proof the exterior of below grade masonry wall in the absence of hydrostatic pressure.

METHODS AND RATE OF APPLICATION

Apply with brush, roller, or spray to dry, dirt-free surface after any cracks have been filled with Roof Cement. On bituminous composition roofs apply 3 to 4 gallons per 100 square feet (1.2 to 1.6 liter per M²). On metal roofs use 2 gallons per 100 square feet (.8 liters per M²). COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	495 POUNDS
5 Gallon Pail	44 POUNDS
1 Gallon (6 to Carton)	54 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	76.0
Volatile Solvent, % by Weight.....	24.0
Mineral Filler and/or other Stabilizers, % by Weight.....	10.0
Asphalt Solids, % by Volume.....	64.0
Water Content, % by Volume	0.05
Net Weight Per Gallon, Pounds	8.3
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon.....	10 Mils
Dry Time @ Recommended Rate of Application.....	3-5 Days
Service Temperature	-30°F to +150°F
Behavior @ 60°C., ASTM D 4479.....	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4479	No Cracking, No Separation
Flash Point, in Degrees F., C.C., ASTM D 93	104 Minimum
Condition in Container	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE(201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com