

#196 BULLDOG® MODIFIED BITUMEN ADHESIVE – TROWEL GRADE

DESCRIPTION

A trowel grade cold process asphalt adhesive for SBS modified bitumen single ply membranes. Its adhesive qualities provide excellent substrate adhesion and strong lap bonds. The manufacturer of this adhesive expects that this product will be used by professional roofing contractors who will employ generally accepted roofing practices in their use of this material.

SPECIFICATIONS: ASTM D 3019, TYPE III

USES

Used as a cold process adhesive to adhere SBS modified bitumen single ply membranes to vertical surfaces. For proper use of this material, please be certain to read label on container and to observe any cautionary statements and instructions provided by the manufacturer of this modified bitumen membrane.

Do not use with modified bitumen single ply membranes with polyethylene or other backing.

May also be used as roof repair cement to asphalt, metal and modified bitumen surfaces.

METHOD and RATE OF APPLICATION

Use a trowel to apply to flashings at about 1/8 inch thickness. Be certain that surface this adhesive is applied to is sound, dry, and dirt free. Use precut and relaxed strips no longer than 15-20 ft. Allow for minimum of 3 in. side laps and 6 in. end laps. Embed membrane while adhesive is wet and allow adhesive to bleed through laps. It is recommended that the membrane be mechanically fastened with a termination bar. Prime parapet walls with BULLDOG Asphalt Primer and allow to dry (approximately 24 hours) before applying Modified Bitumen Adhesive.

COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE

5 Gallon Pail

APPROXIMATE SHIPPING WEIGHTS

46 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight	74.0
Volatile Solvent, % by Weight	26.0
Mineral Filler and/or other Stabilizers, % by Weight	16.0
Water Content, % by Volume	0.05
Net Weight Per Gallon	8.7
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon	77 Mills
Dry Time @ Recommended Rate of Application	2 Days - Outside Shell
Service Temperature	-30°F to + 150°F
Behavior @ 60°C., ASTM D 4586	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4586	No Cracking, No Separation
Flash Point, in Degrees F., C.C., ASTM D 93	104 Minimum
Condition in Container	Homogeneous
Clean-up of Tools	Mineral Spirits or #99 BULLDOG Asphalt Remover

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5th STREET
P.O. BOX 58
BAYONNE, NJ 07002
(201) 339-0855