

## #602AF BULLDOG® SEMI-MASTIC DAMPPROOFING

DESCRIPTION	USES	
<p>A heavy brush grade solvent type coating containing asphalt, solvent and mineral fillers and/or other stabilizers. No heating or thinning of material is required.</p> <p>SPECIFICATIONS: ASTM D 4479, TYPE I</p>	<p>Used to dampproof interior surfaces above grade and exterior surfaces below grade. Demonstrates excellent adhesion when applied to concrete, masonry and steel surfaces. May be used as a base and surface coating in which reinforcing membrane is embedded. This product will impart a highly resistant dampproofing barrier when applied in accordance with manufacturer's instructions and using good application practices. This product may be used as a backup for stone and masonry surfaces. It is recommended that BULLDOG Asphalt Primer be used prior to application.</p>	
METHOD and RATE OF APPLICATION	CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
<p>Apply to a clean, dry surface by brush or spray at a rate of 3 to 4 gallons per 100 square feet (1.2 to 1.6 liters per M<sup>2</sup>). Wait 48 hours before backfilling. For best results apply at 40°F and rising.</p> <p>COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.</p>	<p>55 Gallon Drums</p> <p>5 Gallon Pail</p>	<p>495 POUNDS</p> <p>44 POUNDS</p>

### TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight	76.0
Volatile Solvent, % by Weight	24.0
Mineral Filler and/or other Stabilizer, % by Weight	13.0
Asphalt Solids, % by Volume	67.0
Water Content, % by Volume	0.05
Net Weight Per Gallon, Pounds	8.2
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon	9 Mills
Dry Time @ Recommended Rate of Application	3-5 Days
Service Temperature	-30°F to +150°F
Behavior @ 60°C., ASTM D 4479	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4479	No Cracking, No Separation
Flash Point, in Degrees F., C.C., ASTM D 93	104 Minimum
Condition in Container	Homogeneous
Clean-up of Tools	Mineral Spirits or #99 BULLDOG Asphalt Remover

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

**PALMER ASPHALT COMPANY**  
 196 WEST 5th STREET  
 P.O. BOX 58  
 BAYONNE, NJ 07002  
 (201) 339-0855