

## #603 BULLDOG® NON-FIBERED DAMPPROOFING

DESCRIPTION	USES	
<p>An easily applied liquid coating made with select asphalts and petroleum solvents.</p>	<p>Used in dampproofing applications where a heavy compound is not required and where no reinforcing membrane is intended to be used. Used to dampproof interior surfaces above grade and exterior surfaces below grade. This product demonstrates excellent adhesion when applied to concrete, masonry and steel surfaces.</p>	
METHOD and RATE OF APPLICATION	CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
<p>Apply by brush or spray to clean, dry surface at rate of one gallon per 100 square feet. (.4 liters per M<sup>2</sup>).</p> <p>COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.</p>	<p>55 Gallon Drums</p> <p>5 Gallon Pails</p>	<p>520 POUNDS</p> <p>46 POUNDS</p>

### TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight	73.0
Volatile Solvent, % by Weight	27.0
Asphalt Solids, % by Volume	70.0
Water Content, % by Volume	0.0
Net Weight Per Gallon, Pounds	7.7 lbs.
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon	9 Mils
Dry Time @ Recommended Rate of Application	1 Day
Service Temperature	-30°F to +160°F
Flash Point, in Degrees F., C.C., ASTM D 93	103 Minimum
Finish	Hard, Glossy
Condition in Container	Homogeneous
Clean-up of Tools	Mineral Spirits or #99 BULLDOG Asphalt Remover

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

**DISCLAIMER OF WARRANTIES** . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

**PALMER ASPHALT COMPANY**  
 196 WEST 5th STREET  
 P.O. BOX 58  
 BAYONNE, NJ 07002  
 (201) 339-0855