

#27 BULLDOG® ELASTOMERIC MASTIC



DESCRIPTION

BULLDOG Elastomeric Mastic is a single component, trowel grade, SBS modified asphalt. It forms a rugged rubber-like coating which is extremely flexible and able to accommodate movement. Exhibits excellent low temperature flexibility.

USES

This extremely durable and flexible product can be used for flashings, repairing splits, relining gutters, filling pitch pockets, expansion joints, repairing other modified bitumen systems (e.g. torch type, etc.) and other applications where its ability to withstand movement is useful.

METHODS AND RATE OF APPLICATION

Apply to clean, dry sound surfaces. Remove dust, dirt, water or oil. When applying to metal surfaces and dried out asphalt roofs, prime first with #82 BULLDOG ASPHALT PRIMER which will take approximately 24 hours to dry or #85 BULLDOG QD PRIMER that can dry in as little as one hour. Apply at minimum thickness of 1/8 inch (one gallon per 13 sq. ft.). If reinforcement is needed, use #272 BULLDOG POLYESTER FABRIC. Apply by trowel. All finished BULLDOG ELASTOMERIC MASTIC surfaces should be protected from the sun's ultraviolet rays by surface coating with BULLDOG FIBER ALUMINUM COATING or BULLDOG NON-FIBERED ALUMINUM COATING or BULLDOG ELASTOMERIC EMULSION ROOF COATING. This surface coating should be applied after the BULLDOG ELASTOMERIC MASTIC has weathered at least five days and no later than ten days.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
5 Gallon Pail	43 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

% Solids by Weight	51
Elongation %, ASTM D 412	800
Hardness, Shore A. ASTM D 2240	60
Moisture Vapor Transmission, Perm, ASTM D 1653	0.13
Net Weight Per Gallon	7.9
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon	7 Mils
Dry Time @ Recommended Rate of Application	24 Hours
Service Temperature	-20°F to + 150°F
Handling Precautions	Protect Skin & Eyes & Observe All Cautions on Label
Anticipated Shelf Life	One Year at Room Temperature
Condition in Container	Homogeneous
Clean Up of Tools	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

Copyright © Palmer Asphalt Company 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES. The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE (201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com