

#43AF BULLDOG® MASTIC EMULSION DAMPPROOFING



DESCRIPTION

A trowel grade mastic made with asphalt, water and reinforcing fillers and fibers. It has a smooth paste like consistency that spreads easily and provides an even, quick drying film. SPECIFICATIONS: ASTM D1227, TYPE II, CLASS 1 AND D 1187, TYPE 1

USES

This material is most often used as a dampproofing compound on the exterior of masonry walls above and below grade. It cannot be used when subject to freezing temperatures or rainfall before it thoroughly dries. Used in dampproofing applications to masonry surfaces where a heavy coat is desired. This material may be applied to a new, or "green", damp surface. It requires no heating or thinning prior to application. This product may be used as a base and surface compound in which a reinforcing membrane is embedded.

METHODS AND RATE OF APPLICATION

Apply to a damp surface which is free from grease, dirt and oil. Apply with a trowel or with special mastic spray equipment to thickness of about 1/8 inch at rate of one gallon (3.78 liters) per 13 square feet (1.2M².) Apply at 50°F and rising. Wait 48 hours before backfilling when applied below grade.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	530 POUNDS
5 Gallon Pail	47 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

% Solids by Weight	53.0
Fiber % by Weight	5.6
Water Content, % by Weight.....	47.0 Maximum
Net Weight Per Gallon, Pounds	8.6
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon.....	68 Mills
Dry Time @ Recommended Rate of Application	1 Day-Outside Shell
Condition in Container	May Require Slight Stirring
Storage Precautions.....	Keep From Freezing
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE(201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com