

#45 BULLDOG® FOUNDATION COATING



DESCRIPTION

A heavy brush consistency of non-fibered petroleum base asphalt that requires no heating or thinning before use. Provides excellent dampproofing protection. Not intended to withstand high hydrostatic pressure. If hydrostatic pressure is present use BULLDOG Dampproofing Mastic (#601AF) in conjunction with BULLDOG Asphalt Saturated Cotton Fabric (#201).

USES

Use on substructural and foundation exterior surfaces above or below grade.

METHODS AND RATE OF APPLICATION

On dirt free and dry masonry surface apply a heavy, uniform coat at rate of 2 gallons per 100 square feet (.8 liters per M²). Use brush, roller or spray. DO NOT BACKFILL UNTIL DRY. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	475 POUNDS
5 Gallon Pail	42 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight	72.0
Volatile Solvent, % by Weight.....	28.0
Asphalt Solids, % by Volume.....	72.0
Water Content, % by Volume	0.5
Net Weight Per Gallon, Pounds	7.8
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon9 Mil
Dry Time @ Recommended Rate of Application	2 Days
Service Temperature	-30°F to +130°F
Flash Point, in Degrees F., C.C., ASTM D 93	104
Resistance To Water with Good Drainage	Very Good
Resistance to Water During Submersion	Fair
Condition in Container	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES. The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE (201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com