

#78AF BULLDOG® WET SURFACE ROOF CEMENT



DESCRIPTION

A trowel consistency mastic containing asphalt, petroleum spirits, mineral fibers and/or other stabilizers and chemical additives that enables this product to provide 100% wet surface adhesion when tested in accordance with ASTM D3409. Prevents costly damage to interiors because it will stop most leaks even while rain falls or snow melts. The use of a proprietary trade secret ingredient repels water away from application of this repair cement.

SPECIFICATIONS: ASTM D 4586, TYPE I, CLASS II

USES

Designed for use on wet surfaces to make emergency roof repairs. May also be used on dry surfaces. Will adhere to asphalt, metal and masonry surfaces. May be applied to vertical or horizontal surfaces. Penetrates and adheres under water

METHODS AND RATE OF APPLICATION

When applying to wet surfaces remove as much water as possible. Then apply with trowel, using firm pressure to assure secure bond. On wet surfaces use amount sufficient to stop leak. On dry surfaces apply at a rate of 1/8 inch (3.2 mm.) thickness. (One gallon will cover 13 square feet or 1.2 square meters.)

COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	512 POUNDS
5 Gallon Pail	46 POUNDS
1 Gallon Pail (6 to a Carton)	56 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	78.0
Volatile Solvent, % by Weight.....	22.0
Mineral Filler and/or other Stabilizers, % by Weight.....	18.0
Asphalt Solids, % by Volume.....	61.5
Water Content, % by Volume.....	0.05
Net Weight Per Gallon, Pounds.....	8.7
Dry Film Thickness Without Absorption Applied at Rate of 13 Square Feet Per Gallon.....	77 Mils
Dry Time @ Recommended Rate of Application.....	3 Days - Outside Shell
Service Temperature.....	-30°F to +150°F
Behavior @ 60°C., ASTM D 4586.....	No Sagging, No Blistering
Behavior @ 0°C., ASTM D 4586.....	No Cracking, No Separation
Flash Point, in Degrees F., C.C., ASTM D 93.....	104 Minimum
Wet Surface Adhesion, % ASTM D 3409.....	100
Conditioner in Container.....	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES. The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
 196 WEST 5TH ST
 P.O. BOX 58
 BAYONNE, NJ 07002
 PHONE (201) 339-0855
 FAX (201) 339-8320
www.palmerasphalt.com