

#82 BULLDOG® ASPHALT PRIMER- SPEC GRADE



DESCRIPTION

A light, brush consistency paint-like product made from selected high softening point asphalts and petroleum solvents. It adheres well to a variety of surfaces and dries to touch within 24 hours. SPECIFICATION: ASTM D 41, Type II

USES

Use to prime metal or concrete roof decks before installing built-up roofing and modified bitumen roof membranes. Also used to prime asphalt roofs in new construction or resurfacing applications. Often used to prime masonry surfaces to help create bond prior to use of additional asphaltic dampproofing products or waterproofing systems. THIS PRODUCT IS FOR EXTERIOR USE ONLY.

METHODS AND RATE OF APPLICATION

Apply to a dry and dirt free surface with brush, roller or spray at a rate of one gallon per 100 square feet (.4 liters per M²) on asphalt and masonry surfaces and ¾ gallon per 100 square feet (.3 liters per M²) on metal surfaces. DO NOT THIN. COVER AIR INTAKES BEFORE APPLYING AND WHILE CURING. EMPTY CONTENTS BEFORE DISPOSING OF PAIL.

CONTAINER SIZE	APPROXIMATE SHIPPING WEIGHTS
55 Gallon Drum	475 POUNDS
5 Gallon Pail	42 POUNDS
1 Gallon (6 to Carton)	52 POUNDS

TYPICAL PHYSICAL CHARACTERISTICS

Nonvolatile Matter, % Solids by Weight.....	63.0
Volatile Solvent, % by Weight.....	37.0
Asphalt Solids, % by Volume.....	63.0
Water Content, % by Volume.....	0.0
Net Weight Per Gallon, Pounds.....	7.7
Dry Film Thickness Without Absorption Applied at Rate of 100 Square Feet Per Gallon.....	.8 Mills
Dry Time @ Recommended Rate of Application.....	1 Day
Service Temperature.....	-30°F to +160°F
Flash Point, in Degrees F., C.C., ASTM D 93.....	104 Minimum
Penetration @ 77°F, 100 g/5 Sec.....	26
Condition in Container.....	Homogeneous
Clean Up of Tools.....	Use Mineral Spirits or #99 BULLDOG Asphalt Remover

COPYRIGHT © PALMER ASPHALT COMPANY 4-08

The typical characteristics shown for this product are based upon the average of test results conducted on the finished product and on the raw material components used. They are subject to production variations and may be changed without notice. All other information contained on this sheet is to be used as a guide. For proper use and application please observe instructions and cautions on container.

DISCLAIMER OF WARRANTIES . The application procedures and other information contained herein or on any other literature or on the labels of any of our products is intended to provide a guide for the general use, handling, and storage of products produced by Palmer Asphalt Company and is based upon ideas that are well tested and believed to be reliable. Palmer Asphalt Company hereby disclaims all warranties, either expressed or implied, since it cannot control workmanship, weather, quality of other materials used, and other variables that might affect the results. Liability under this warranty is limited to the replacement of our material or refund of its cost at our option. This Company does not authorize any agent or any representative to make any warranty.

PALMER ASPHALT COMPANY
196 WEST 5TH ST
P.O. BOX 58
BAYONNE, NJ 07002
PHONE(201) 339-0855
FAX (201) 339-8320
www.palmerasphalt.com